

I. Chorkendorff, J. W. Niemantsverdriet

Concepts of Modern Catalysis and Kinetics



WILEY-
VCH

WILEY-VCH GmbH & Co. KGaA

I. Chorkendorff, J. W. Niemantsverdriet
**Concepts of Modern Catalysis
and Kinetics**

Also of Interest:

Niemantsverdriet, J. W.

Spectroscopy in Catalysis

An Introduction

Second, Completely Revised Edition

2000

3-527-30200-X

Hagen, J., Hawkins, S.

Industrial Catalysis

A Practical Approach

1999

ISBN 3-527-29528-3

Thomas, J. M., Thomas, W. J.

Principles and Practice of Heterogeneous Catalysis

1996

ISBN 3-527-29239-X

Green, M. M., Wittcoff, H.

Organic Chemistry Principles and Industrial Practice

2003

ISBN 3-527-30289-1

Wijngaarden, R. I., Westerterp, K. R., Kronberg, A.

Industrial Catalysis

Optimizing Catalysts and Processes

1998

ISBN 3-527-28581-4

I. Chorkendorff, J. W. Niemantsverdriet

Concepts of Modern Catalysis and Kinetics



WILEY-
VCH

WILEY-VCH GmbH & Co. KGaA

Prof. Dr. I. Chorkendorff

Technical University of Denmark
Interdisciplinary Research Center for Catalysis (ICAT)
Building 312
DK 2800 Lyngby
Denmark

Prof. Dr. J. W. Niemantsverdriet

Eindhoven University of Technology
Schuit Institute of Catalysis
NL 5600 MB Eindhoven
The Netherlands

Cover illustration

Artistic view of surface reaction and potential energy barriers. Painted by Ove Broo, reproduced with kind permission.

■ This book was carefully produced. Nevertheless, authors and publisher do not warrant the information contained therein to be free of errors. Readers are advised to keep in mind that statements, data, illustrations, procedural details or other items may inadvertently be inaccurate.

Library of Congress Card No.:

Applied for.

British Library Cataloguing-in-Publication Data

A catalogue record for this book is available from the British Library.

**Bibliographic information published by
Die Deutsche Bibliothek**

Die Deutsche Bibliothek lists this publication in the Deutsche Nationalbibliografie, detailed bibliographic data is available in the Internet at <<http://dnb.ddb.de>>.

© 2003 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim

All rights reserved (including those of translation in other languages). No part of this book may be reproduced in any form – by photoprinting, microfilm, or any other means – nor transmitted or translated into a machine language without written permission from the publisher. Registered names, trademarks, etc. used in this book, even when not specifically marked as such, are not to be considered unprotected by law.

Printed in the Federal Republic of Germany
Printed on acid-free paper.

Composition Kühn & Weyh, Freiburg
Printing Strauss Offsetdruck, Mörlenbach
Bookbinding Litges & Dopf Buchbinderei GmbH, Heppenheim

ISBN 3-527-30574-2

To Ina and Camilla

*To Marianne, Hanneke,
Annemieke, Karin and Peter*

Contents

1	Introduction to Catalysis	1
1.1	What is Catalysis?	2
1.2	Catalysts Can Be Atoms, Molecules, Enzymes and Solid Surfaces	4
1.2.1	Homogeneous Catalysis	4
1.2.2	Biocatalysis	5
1.2.3	Heterogeneous Catalysis	6
1.3	Why is Catalysis Important?	8
1.3.1	Catalysis and Green Chemistry	8
1.3.2	Atom Efficiency, <i>E</i> Factors and Environmental Friendliness	9
1.3.3	The Chemical Industry	11
1.4	Catalysis as a Multidisciplinary Science	16
1.4.1	The Many Length Scales of a “Catalyst”	16
1.4.2	Time Scales in Catalysis	17
1.5	The Scope of This Book	18
1.6	Catalysis in Journals	18
1.7	General References to Textbooks in Catalysis	21
2	Kinetics	23
2.1	Introduction	23
2.2	The Rate Equation and Power Rate Laws	25
2.3	Reactions and Thermodynamic Equilibrium	28
2.3.1	Example of Chemical Equilibrium: The Ammonia Synthesis	31
2.3.2	Chemical Equilibrium for a Non-ideal Gas	34
2.4	Temperature Dependence of the Rate	36
2.5	Integrated Rate Equations: Time Dependence of Concentrations in Reactions of Different Orders	38
2.6	Coupled Reactions in Flow Reactors: The Steady-state Approximation	41
2.7	Coupled Reactions in Batch Reactors	45
2.8	Catalytic Reactions	48
2.8.1	The Mean-field Approximation	52
2.9	Langmuir Adsorption Isotherms	53
2.9.1	Associative Adsorption	53
2.9.2	Dissociative Adsorption	55

2.9.3	Competitive Adsorption	55
2.10	Reaction Mechanisms	56
2.10.1	Langmuir–Hinshelwood or Eley–Rideal Mechanisms	56
2.10.2	Langmuir–Hinshelwood Kinetics	57
2.10.3	The Complete Solution	58
2.10.4	The Steady State Approximation	59
2.10.5	The Quasi-equilibrium Approximation	59
2.10.6	Steps with Similar Rates	61
2.10.7	Irreversible Step Approximation	61
2.10.8	The MARI Approximation	62
2.10.9	Nearly Empty Surface	62
2.10.10	Reaction Order	63
2.10.11	Apparent Activation Energy	65
2.11	Entropy, Entropy Production, Auto Catalysis and Oscillating Reactions	69
2.12	Kinetics of Enzyme-catalyzed Reactions	73
3	Reaction Rate Theory	79
3.1	Introduction	79
3.2	The Boltzmann Distribution and the Partition Function	80
3.3	Partition Functions of Atoms and Molecules	83
3.3.1	The Boltzmann Distribution	84
3.3.1.1	Justification for Equating λ_2 with $1/T$	86
3.3.2	Maxwell–Boltzmann Distribution of Velocities	86
3.3.3	Total Partition Function of System	87
3.3.3.1	Translational Partition Function	88
3.3.3.2	Vibrational Partition Function	89
3.3.3.3	Rotational (and Nuclear) Partition Function	90
3.3.3.4	Electronic and Nuclear Partition Functions	92
3.4	Molecules in Equilibrium	94
3.5	Collision Theory	100
3.5.1	Rate of Surface Collisions	103
3.5.2	Reaction Probability	104
3.5.3	Fundamental Objection Against Collision Theory	106
3.6	Activation of Reacting Molecules by Collisions: The Lindemann Theory	106
3.7	Transition State Theory	108
3.7.1	Thermodynamic Form of the Rate Transition State Expression	110
3.8	Transition State Theory of Surface Reactions	113
3.8.1	Adsorption of Atoms	113
3.8.1.1	Indirect Adsorption	114
3.8.1.2	Direct Adsorption	116
3.8.2	Adsorption of Molecules	119
3.8.2.1	Precursor-mediated or Indirect Adsorption	119

3.8.2.2	Direct Adsorption	120
3.8.3	Reaction Between Adsorbates	122
3.8.4	Desorption of Molecules	123
3.9	Summary	126
4	Catalyst Characterization	129
4.1	Introduction	129
4.2	X-Ray Diffraction (XRD)	131
4.3	X-ray Photoelectron Spectroscopy (XPS)	134
4.4	Extended X-Ray Absorption Fine Structure (EXAFS)	139
4.5	Electron Microscopy	143
4.6	Mössbauer Spectroscopy	147
4.7	Ion Spectroscopy: SIMS, LEIS, RBS	150
4.8	Temperature-programmed Reduction, Oxidation and Sulfidation	154
4.9	Infrared Spectroscopy	155
4.10	Surface Science Techniques	158
4.10.1	Low Energy Electron Diffraction (LEED)	158
4.10.2	Scanning Probe Microscopy	161
4.10.2.1	Scanning Tunneling Microscopy (STM)	161
4.10.2.2	The Atomic Force Microscope (AFM)	164
4.11	Concluding Remarks	166
5	Solid Catalysts	167
5.1	Requirements of a Successful Catalyst	167
5.2	Structure of Metals, Oxides and Sulfides and their Surfaces	168
5.2.1	Metal Structures	168
5.2.2	Surface Crystallography of Metals	168
5.2.2.1	Crystal Planes	169
5.2.2.2	Adsorbate Sites	171
5.2.2.3	The Two-dimensional Lattice	172
5.2.3	Oxides and Sulfides	174
5.2.4	Surface Free Energy	177
5.3	Characteristics of Small Particles and Porous Material	178
5.3.1	Wulff Construction	180
5.3.2	Pore System	182
5.3.3	Surface Area	183
5.4	Catalyst Supports	189
5.4.1	Silica	190
5.4.2	Alumina	192
5.4.3	Carbon	194
5.4.4	Shaping of Catalyst Supports	194
5.5	Preparation of Supported Catalysts	195
5.5.1	Coprecipitation	195
5.5.2	Impregnation, Adsorption and Ion-exchange	196
5.5.3	Deposition Precipitation	198

5.6	Unsupported Catalysts	198
5.7	Zeolites	199
5.7.1	Structure of a Zeolite	200
5.7.2	Compensating Cations and Acidity	201
5.7.3	Applications of Zeolites	202
5.8	Catalyst Testing	203
5.8.1	Ten Commandments for Testing Catalysts	204
5.8.2	Activity Measurements	206
5.8.2.1	Transport Limitations and the Thiele Diffusion Modulus	206
5.8.2.2	Pore Diffusion	211
5.8.2.3	Consequences of Transport Limitations for Testing Catalysts	213
6	Surface Reactivity	215
6.1	Introduction	215
6.2	Physisorption	215
6.2.1	The Van der Waals Interaction	216
6.2.2	Including the Repulsive Part	217
6.3	Chemical Bonding	218
6.3.1	Bonding in Molecules	219
6.3.1.1	Diatomic Molecule	219
6.3.1.2	Homonuclear Diatomic Molecules	220
6.3.1.3	Heteronuclear System	222
6.3.2	The Solid Surface	223
6.3.2.1	Work Function	225
6.3.2.2	Free Electron Gas and the Jellium Model	226
6.3.2.3	Tight Binding Model	229
6.3.2.4	Simple Model of a Transition Metal	233
6.4	Chemisorption	235
6.4.1	Newns–Anderson Model	236
6.4.1.1	Case 1: Atom on a Metal of Constant Electron Density	239
6.4.1.2	Case 2: Atom on an sp Metal	240
6.4.1.3	Case 3: Atom on a Transition Metal	241
6.4.2	Summary of Newns–Anderson Approximation in Qualitative Terms	242
6.4.2.1	Adsorption on a Free-electron Metal	242
6.4.2.2	Atomic Adsorption on a Transition or d Metal	242
6.4.2.3	Adsorption of a Molecule on a Transition Metal	243
6.4.3	Electrostatic Effects in Atomic Adsorbates on Jellium	244
6.5	Important Trends in Surface Reactivity	246
6.5.1	Trend in Atomic Chemisorption Energies	246
6.5.2	Trends in Molecular Chemisorption	250
6.5.2.1	Effects of Stress and Strain on Chemisorption	252
6.5.3	Trends in Surface Reactivity	254
6.5.3.1	Physisorption, Chemisorption and Dissociation	254
6.5.3.2	Dissociative Adsorption: N ₂ on Ruthenium Surfaces	255
6.5.3.3	Trends in Dissociative Adsorption	256

6.5.3.4	Transition States and the Effect of Coverage: Ethylene Hydrogenation	258
6.5.3.5	Sabatier's Principle	261
6.5.3.6	Opportunities for Tuning Surface Reactivity	262
6.5.4	Universality in Heterogeneous Catalysis	263
7	Kinetics of Reactions on Surfaces	267
7.1	Elementary Surface Reactions	267
7.1.1	Adsorption and Sticking	267
7.1.1.1	Determination of Sticking Coefficients	268
7.1.2	Desorption	274
7.1.2.1	Quantitative Interpretation of TPD Data	276
7.1.2.2	Compensation Effect in Temperature Programmed Desorption	278
7.1.3	Lateral Interactions in Surface Reactions	279
7.1.4	Dissociation Reactions on Surfaces	282
7.1.5	Intermediates in Surface Reactions	285
7.1.6	Association Reactions	285
7.2	Kinetic Parameters from Fitting Langmuir–Hinshelwood Models	288
7.3	Micro-kinetic Modeling	290
7.3.1	Reaction Scheme and Rate Expressions	291
7.3.2	Activation Energy and Reaction Orders	293
7.3.3	Ammonia Synthesis Catalyst under Working Conditions	297
8	Heterogeneous Catalysis in Practice: Hydrogen	301
8.1	Introduction	301
8.2	Steam Reforming Process	301
8.2.1	Basic Concepts of the Process	301
8.2.1	Mechanistic Details of Steam Reforming	304
8.2.3	Challenges in the Steam Reforming Process	305
8.2.4	The SPARG Process: Selective Poisoning by Sulfur	307
8.2.5	Gold–Nickel Alloy Catalysts for Steam Reforming	308
8.2.6	Direct Uses of Methane	309
8.2.6.1	Direct Methanol Formation	310
8.2.6.2	Catalytic Partial Oxidation of Methane	311
8.3	Reactions of Synthesis Gas	311
8.3.1	Methanol Synthesis	311
8.3.1.1	Basic Concepts of the Process	311
8.3.1.2	Methanol Directly Synthesized from CO and H ₂	319
8.3.2	Fischer–Tropsch Process	323
8.4	Water Gas Shift Reaction	325
8.5	Synthesis of Ammonia	327
8.5.1	History of Ammonia Synthesis	327
8.5.2	Ammonia Synthesis Plant	329
8.5.3	Operating the Reactor	331
8.5.4	Scientific Rationale for Improving Catalysts	333

- 8.6 Promoters and Inhibitors 335
- 8.7 The “Hydrogen Society” 338
 - 8.7.1 The Need for Sustainable Energy 338
 - 8.7.2 Sustainable Energy Sources 340
 - 8.7.3 Hydrogen and Fuel Cells 341
 - 8.7.3.1 The Proton Exchange Membrane Fuel Cell (PEMFC) 342
 - 8.7.3.2 Solid Oxide Fuel Cell 345
 - 8.7.3.3 Efficiency of Fuel Cells 345
 - 8.7.3.4 Hydrogen Storage and Transportation 347

- 9 Oil Refining and Petrochemistry 349**
 - 9.1 Crude Oil 349
 - 9.2 Hydrotreating 353
 - 9.2.1 Heteroatoms and Undesired Compounds 353
 - 9.2.2 Hydrotreating Catalysts 355
 - 9.2.3 Hydrodesulfurization Reaction Mechanisms 357
 - 9.3 Gasoline Production 360
 - 9.3.1 Fluidized Catalytic Cracking 361
 - 9.3.2 Reforming and Bifunctional Catalysis 364
 - 9.3.3 Alkylation 368
 - 9.4 Petrochemistry: Reactions of Small Olefins 370
 - 9.4.1 Ethylene Epoxidation 370
 - 9.4.2 Partial Oxidation and Ammoxidation of Propylene 372
 - 9.4.3 Polymerization Catalysis 374

- 10 Environmental Catalysis 377**
 - 10.1 Introduction 377
 - 10.2 Automotive Exhaust Catalysis 377
 - 10.2.1 The Three-way Catalyst 379
 - 10.2.1.1 Catalytic Converter 381
 - 10.2.1.2 Demonstration Experiments 384
 - 10.2.1.3 Catalyst Deactivation 384
 - 10.2.2 Catalytic Reactions in the Three-way Catalyst: Mechanism and Kinetics 385
 - 10.2.2.1 CO Oxidation Reaction 385
 - 10.2.2.2 Is CO Oxidation a Structure-insensitive Reaction? 387
 - 10.2.2.3 CO + NO Reaction 388
 - 10.2.2.4 CO + NO Reaction at Higher Pressures 390
 - 10.2.2.5 Reactions Involving Hydrocarbons 391
 - 10.2.2.6 NO_x Storage–Reduction Catalyst for Lean-burning Engines 391
 - 10.2.3 Concluding Remarks on Automotive Catalysts 393
 - 10.3 Air Pollution by Large Stationary Sources 393
 - 10.3.1 Selective Catalytic Reduction: The SCR Process 393
 - 10.3.1.1 Catalyst for the SCR Process 395

10.3.3.2 SCR Reaction Kinetics 396
10.3.2 SCR Process for Mobile Units 400

Questions and Exercises 401


Appendix A 443

Index 447

Preface

Catalysis: conceptually understood but far away from maturity

Catalysis as a phenomenon is becoming reasonably well understood on a conceptual level. Recognized as a phenomenon and utilized around 1816 by Davy in the mine safety lamp, and defined around 1835 by Berzelius, catalysis obtained an extensive empirical basis by the systematic experiments of Mitschlich in the early 20th century. Studies of catalytic mechanisms became feasible when Langmuir – Hinshelwood kinetics became available in the mid 1920s. Since then, for many decades fundamental catalysis became more or less synonymous with kinetic analysis. The advent of spectroscopy, starting with infrared spectroscopy in the late 1950s, followed by a range of other techniques for catalyst characterization and investigation of surface species opened the opportunity to relate catalytic properties with composition and structure of materials. Surface science enabled one to resolve adsorption geometries and reactivity patterns in well-defined structures, culminating in scanning tunneling spectroscopy as the ultimate tool to resolve surface structure and adsorbed spe-



cies with atomic precision by the end of the 20th century. Techniques have become available to study catalysts under working conditions. Ever increasing computational power enables the calculation of adsorbate geometries, bond strengths and even reaction rates. Anno 2003, catalysis has developed into a scientific discipline with a firm conceptual basis. The relation between catalytic activity for a certain reaction and the composition, structure of a surface is in general qualitatively well understood, provided the surfaces are relatively simple and defined.

However, the prospect of designing a catalyst from first principles behind our desk is still far away. A number of reasons is responsible. Although we may be able to describe a catalytic reaction on a well-defined single crystal of a metal under well-defined and simplified conditions, this becomes tremendously more complicated when the same reaction runs over small catalyst particles on a support in a realistic reactor environment. The world of the ideal surface science laboratory and that of industrial practice are not only separated by the often cited pressure gap, but also by structural, and materials gaps. The complexity of small, supported crystallites that dynamically respond to every change in reaction environment is only beginning to be explored. Secondly, the way we describe the kinetics of catalytic reactions is, albeit greatly refined, still based on the adsorption isotherm of Langmuir (1915) and the kinetic formalism of Hinshelwood (1927), based on ideal surfaces with equivalent adsorption sites and adsorbate species that are randomly mixed and do not interact. This represents another gross over simplification, which has recently become recognized and is beginning to become addressed in terms of ensembles with reactivities many orders of magnitude more reactive than the planar surfaces.

This book intends to be an introduction to the fundamentals of heterogeneous catalysis, aiming to explain the phenomenon of catalysis on a conceptual level. Kinetics, being the tool to investigate and describe catalytic reactivity as it expresses itself in a reactor, plays an important role in this book. Also reaction rate theory, providing the formalism to relate reaction rates to molecular structure of reacting species is described extensively. Next we describe catalytic surfaces, as well as the tools to study them. With this knowledge we treat surface reactivity in greatly simplified molecular orbital theory, again with the aim to give a conceptual explanation of how a catalyst works and what are the trends when going from one surface/structure to another. The final chapters serve to illustrate catalysis in practice, to give the reader an impression of how catalysis is applied. We emphasize that the book is a textbook, written for students in chemistry, physics and chemical engineering who are interested in understanding the concepts. Many more important details are worthwhile knowing, but are beyond the scope of this book and will have to be found in specialist literature.

This book is based on courses, which the authors have taught at Lyngby and Eindhoven for many years. For example, Chapters 1–3 form the basis for a mandatory course “Kinetics and Catalysis” presented in the second year of the Bachelor’s curriculum at Eindhoven, while Chapters 4,5 and 8–10 formed the basis for an optional course Introduction to Catalysis. In Lyngby, Chapters 1–7 have been used for an optional course in “Chemical Reaction Kinetics and Catalysis” in the Master’s curriculum. At the end of the book we have added a list of questions for every chapter,

which students may use to test their knowledge. The exercises are mainly meant to enable students to acquire skills in kinetic modelling. Some of these exercises have been used in written examinations. We intend to make solutions available on our web sites (www.icat.dtu.dk and www.catalysis.nl).

The authors are indebted to many colleagues in the field of catalysis and surface science. We mention in particular Jens Nørskov and Rutger van Santen. Both made very substantial contributions to the theory of heterogeneous catalysis. We are very grateful for the many extensive and pleasant discussions we had with them. Also our contacts with industry have been most inspiring and indispensable. We mention in particular Haldor Topsøe A/S in Lyngby and the Shell Research and Technology Centre in Amsterdam. We also want to thank the numerous students who followed our courses in Lyngby and Eindhoven. They have taught us more than they perhaps realize. Finally we thank our families who patiently allowed us to spend a considerable amount of time on this book. We devote this book to them.

Lyngby/Eindhoven
June 2003

Ib Chorkendorff
Hans Niemantsverdriet

1

Introduction to Catalysis

Ask the average person in the street what a catalyst is, and he or she will probably tell you that a catalyst is what one has under the car to clean up the exhaust. Indeed, the automotive exhaust converter represents a very successful application of catalysis; it does a great job in removing most of the pollutants from the exhaust leaving the engines of cars. However, catalysis has a much wider scope of application than abating pollution.

Catalysis in Industry

Catalysts are the workhorses of chemical transformations in the industry. Approximately 85–90% of the products of chemical industry are made in catalytic processes. Catalysts are indispensable in

- Production of transportation fuels in one of the approximately 440 oil refineries all over the world
- Production of bulk and fine chemicals in all branches of chemical industry
- Prevention of pollution by avoiding formation of waste (unwanted byproducts)
- Abatement of pollution in end-of-pipe solutions (automotive and industrial exhaust)

A catalyst offers an alternative, energetically favorable mechanism to the non-catalytic reaction, thus enabling processes to be carried out under industrially feasible conditions of pressure and temperature.

For example, living matter relies on enzymes, which are the most specific catalysts one can think of. Also, the chemical industry cannot exist without catalysis, which is an indispensable tool in the production of bulk chemicals, fine chemicals and fuels.

For scientists and engineers catalysis is a tremendously challenging, highly multi-disciplinary field. Let us first see what catalysis is, and then why it is so important for mankind.

1.1

What is Catalysis?

A catalyst accelerates a chemical reaction. It does so by forming bonds with the reacting molecules, and by allowing these to react to a product, which detaches from the catalyst, and leaves it unaltered such that it is available for the next reaction. In fact, we can describe the catalytic reaction as a cyclic event in which the catalyst participates and is recovered in its original form at the end of the cycle.

Let us consider the catalytic reaction between two molecules A and B to give a product P, see Fig. 1.1. The cycle starts with the bonding of molecules A and B to the catalyst. A and B then react within this complex to give a product P, which is also bound to the catalyst. In the final step, P separates from the catalyst, thus leaving the reaction cycle in its original state.




Figure 1.1. Every catalytic reaction is a sequence of elementary steps, in which reactant molecules bind to the catalyst, where they react, after which the product detaches from the catalyst, liberating the latter for the next cycle.

To see how the catalyst accelerates the reaction, we need to look at the potential energy diagram in Fig. 1.2, which compares the non-catalytic and the catalytic reaction. For the non-catalytic reaction, the figure is simply the familiar way to visualize the Arrhenius equation: the reaction proceeds when A and B collide with sufficient energy to overcome the activation barrier in Fig. 1.2. The change in Gibbs free energy between the reactants, A + B, and the product P is ΔG .

The catalytic reaction starts by bonding of the reactants A and B to the catalyst, in a spontaneous reaction. Hence, the formation of this complex is exothermic, and the free energy is lowered. There then follows the reaction between A and B while they are bound to the catalyst. This step is associated with an activation energy; however, it is significantly lower than that for the uncatalyzed reaction. Finally, the product P separates from the catalyst in an endothermic step.




Figure 1.2. Potential energy diagram of a heterogeneous catalytic reaction, with gaseous reactants and products and a solid catalyst. Note that the uncatalyzed reaction has to overcome a substantial energy barrier, whereas the barriers in the catalytic route are much lower.

The energy diagram of Fig. 1.2 illustrates several important points:

- The catalyst offers an alternative path for the reaction, which is obviously more complex, but energetically much more favorable.
- The activation energy of the catalytic reaction is significantly smaller than that of the uncatalyzed reaction; hence, the rate of the catalytic reaction is much larger (we explain this in greater detail in Chapter 2).
- The overall change in free energy for the catalytic reaction equals that of the uncatalyzed reaction. Hence, the catalyst does not affect the equilibrium constant for the overall reaction of $A + B$ to P . Thus, if a reaction is thermodynamically unfavorable, a catalyst cannot change this situation. A catalyst changes the kinetics but *not* the thermodynamics.
- The catalyst accelerates both the forward and the reverse reaction to the same extent. In other words, if a catalyst accelerates the formation of the product P from A and B , it will do the same for the decomposition of P into A and B .

Thus far it is immediately evident that there are also cases in which the combination of catalyst with reactants or products will not be successful:

- If the bonding between reactants and catalyst is too weak, there will be hardly any conversion of A and B into products.
- Conversely if the bond between the catalyst and one of the reactants, say A , is too strong, the catalyst will be mostly occupied with species A , and B is not available to form the product. If A and B both form strong bonds with the catalyst, the intermediate situation with A or B on the catalyst may be so stable that

reaction becomes unlikely. In terms of Fig. 1.2, the second level lies so deep that the activation energy to form P on the catalyst becomes too high. The catalyst is said to be poisoned by (one of) the reactants.

- In the same way, the product P may be too strongly bound to the catalyst for separation to occur. In this case the product poisons the catalyst.

Hence, we intuitively feel that the successful combination of catalyst and reaction is that in which the interaction between catalyst and reacting species is not too weak, but also not too strong. This is a loosely formulated version of Sabatier's Principle, which we encounter in a more precise form in Chapter 2 and in detail in Section 6.5.3.5.

Until now, the catalyst has been an unspecified, abstract body, so let us first look at what kind of catalysts exist.

1.2

Catalysts Can Be Atoms, Molecules, Enzymes and Solid Surfaces



Catalysts come in a multitude of forms, varying from atoms and molecules to large structures such as zeolites or enzymes. In addition they may be employed in various surroundings: in liquids, gases or at the surface of solids. Preparing a catalyst in the optimum form and studying its precise composition and shape are an important specialism, which we describe in later chapters.

It is customary to distinguish the following three subdisciplines in catalysis: homogeneous, heterogeneous and bio catalysis. We illustrate each with an example.


1.2.1

Homogeneous Catalysis

In homogeneous catalysis, both the catalyst and the reactants are in the same phase, i.e. all are molecules in the gas phase, or, more commonly, in the liquid phase. One of the simplest examples is found in atmospheric chemistry. Ozone in the atmosphere decomposes, among other routes, via a reaction with chlorine atoms:




or overall



Ozone can decompose spontaneously, and also under the influence of light, but a Cl atom accelerates the reaction tremendously. As it leaves the reaction cycle unaltered, the Cl atom is a catalyst. Because both reactant and catalyst are both in the same phase, namely the gas phase, the reaction cycle is an example of homogeneous

catalysis. (This reaction was historically important in the prediction of the ozone hole.)

Industry uses a multitude of homogenous catalysts in all kinds of reactions to produce chemicals. The catalytic carbonylation of methanol to acetic acid




by $[\text{Rh}(\text{CO})_2\text{I}_2]^-$ complexes in solution is one of many examples. In homogeneous catalysis, often aimed at the production of delicate pharmaceuticals, organometallic complexes are synthesized in procedures employing molecular control, such that the judicious choice of ligands directs the reacting molecules to the desired products.

1.2.2

Biocatalysis

Enzymes are nature's catalysts. For the moment it is sufficient to consider an enzyme as a large protein, the structure of which results in a very shape-specific active site (Fig. 1.3). Having shapes that are optimally suited to guide reactant molecules (usually referred to as substrates) in the optimum configuration for reaction, enzymes are highly specific and efficient catalysts. For example, the enzyme catalase catalyzes the decomposition of hydrogen peroxide into water and oxygen



at an incredibly high rate of up to 10^7 hydrogen peroxide molecules per second!




Figure 1.3. Schematic representation of an enzyme-catalyzed reaction. Enzymes often match the shape of the substrates they bind to, or the transition state of the reaction they catalyze. Enzymes are highly efficient catalysts and represent a great source of inspiration for designing technical catalysts.

Enzymes allow biological reactions to occur at the rates necessary to maintain life, such as the build up of proteins and DNA, or the breakdown of molecules and the storage of energy in sugars. An example with, perhaps, some special appeal to students is the breakdown of alcohol to acetaldehyde inside the body by the enzyme alcohol dehydrogenase. The acetaldehyde in turn is converted into acetate by aldehyde hydrogenase. Some people cannot tolerate alcohol (as revealed by facial flushing after drinking a small amount) because they lack the form of the enzyme that breaks down acetaldehyde.

1.2.3

Heterogeneous Catalysis

In heterogeneous catalysis, solids catalyze reactions of molecules in gas or solution. As solids – unless they are porous – are commonly impenetrable, catalytic reactions occur at the surface. To use the often expensive materials (e.g. platinum) in an economical way, catalysts are usually nanometer-sized particles, supported on an inert, porous structure (see Fig. 1.4). Heterogeneous catalysts are the workhorses of the chemical and petrochemical industry and we will discuss many applications of heterogeneous catalysis throughout this book.






Figure 1.4. Catalysts are nanomaterials and catalysis is nanotechnology. If we define nanotechnology as the branch of materials science aiming to control material properties on the nanometer scale, then catalysis represents a field where nanomaterials have been applied commercially for about a century. Many synthetic techniques are available to

produce small particles for heterogeneous catalysts, and to keep them sufficiently stable so that they can withstand the often hostile conditions of an industrial reactor. Modern catalysis is preeminently nanotechnology. [Figure adapted from A.K. Datye and N.J. Long, *Ultramicroscopy* **25** (1988) 203.]

As an introductory example we take one of the key reactions in cleaning automotive exhaust, the catalytic oxidation of CO on the surface of noble metals such as platinum, palladium and rhodium. To describe the process, we will assume that the metal surface consists of active sites, denoted as “*.” We define them properly later on. The catalytic reaction cycle begins with the adsorption of CO and O₂ on the surface of platinum, whereby the O₂ molecule dissociates into two O atoms (X* indicates that the atom or molecule is adsorbed on the surface, i.e. bound to the site *):



The adsorbed O atom and the adsorbed CO molecule then react on the surface to form CO₂, which, being very stable and relatively unreactive, interacts only weakly with the platinum surface and desorbs almost instantaneously:



Note that in the latter step the adsorption sites on the catalyst are liberated, so that these become available for further reaction cycles. Figure 1.5 shows the reaction cycle along with a potential energy diagram.




Figure 1.5. Reaction cycle and potential energy diagram for the catalytic oxidation of CO by O₂.

Where in this cycle is the essential influence of the catalyst? Suppose we carry out the reaction in the gas phase without a catalyst. The reaction will proceed if we raise the temperature sufficiently for the O₂ molecule to dissociate into two O atoms (radicals). Once these radicals are available, the reaction with CO to CO₂ follows instantaneously.

The activation energy of the gas phase reaction will be roughly equal to the energy required to split the strong O–O bond in O₂, i.e. about 500 kJ mol⁻¹. In the catalytic reaction, however, the O₂ molecule dissociates easily – in fact without an activation energy – on the surface of the catalyst. The activation energy is associated with the reaction between adsorbed CO and O atoms, which is of the order of 50–100 kJ mol⁻¹. Desorption of the product molecule CO₂ costs only about 15–30 kJ mol⁻¹ (depending on the metal and its surface structure). Hence if we compare the catalytic and the uncatalyzed reaction, we see that the most difficult step of the homogeneous gas phase reaction, namely the breaking of the O–O bond is easily performed by the catalyst. Consequently, the ease with which the CO₂ molecule forms determines the rate at which the overall reaction from CO and O₂ to CO₂ proceeds. This is a very general situation for catalyzed reactions, hence the expression: A catalyst breaks bonds, and lets other bonds form. The beneficial action of the catalyst is in the dissociation of a strong bond, the subsequent steps might actually proceed faster without the catalyst (which is a hypothetical situation of course). In Chapter 6 we analyze in detail how a surface induces the breaking of intramolecular bonds.

1.3

Why is Catalysis Important?

The chemical industry of the 20th century could not have developed to its present status on the basis of non-catalytic, stoichiometric reactions alone. Reactions can in general be controlled on the basis of temperature, concentration, pressure and contact time. Raising the temperature and pressure will enable stoichiometric reactions to proceed at a reasonable rate of production, but the reactors in which such conditions can be safely maintained become progressively more expensive and difficult to make. In addition, there are thermodynamic limitations to the conditions under which products can be formed, e.g. the conversion of N₂ and H₂ into ammonia is practically impossible above 600 °C. Nevertheless, higher temperatures are needed to break the very strong N≡N bond in N₂. Without catalysts, many reactions that are common in the chemical industry would not be possible, and many other processes would not be economical.

Catalysts accelerate reactions by orders of magnitude, enabling them to be carried out under the most favorable thermodynamic regime, and at much lower temperatures and pressures. In this way efficient catalysts, in combination with optimized reactor and total plant design, are the key factor in reducing both the investment and operation costs of a chemical processes. But that is not all.

1.3.1

Catalysis and Green Chemistry

Technology is called “green” if it uses raw materials efficiently, such that the use of toxic and hazardous reagents and solvents can be avoided while formation of waste or undesirable byproducts is minimized. Catalytic routes often satisfy these criteria.

A good example is provided by the selective oxidation of ethylene to ethylene epoxide, an important intermediate towards ethylene glycol (antifreeze) and various polyethers and polyurethanes (Fig. 1.6).






Figure 1.6. Ethylene epoxide, an important intermediate in the chemical industry.

The old, non-catalytic route (called the epichlorohydrin process) follows a three-step synthesis:



or in total:



Hence, for every molecule of ethylene oxide, 1 molecule of salt is formed, creating a waste problem that was traditionally solved by dumping it in a river. Such practice is of course now totally unacceptable.

The catalytic route, however, is simple and clean, although it does produce a small amount of CO_2 . Using silver, promoted by small amounts of chlorine, as the catalyst, ethylene oxide is formed directly from C_2H_4 and O_2 at a selectivity of around 90%, with about 10% of the ethylene ending up as CO_2 . Nowadays all production facilities for ethylene oxide use catalysts.

1.3.2


Atom Efficiency, E Factors and Environmental Friendliness

Numerous organic syntheses are based on stoichiometric oxidations of hydrocarbons with sodium dichromate and potassium permanganate, or on hydrogenations with alkali metals, borohydrides or metallic zinc. In addition, there are reactions


such as aromatic nitrations with H_2SO_4 and HNO_3 , or acylations with AlCl_3 that generate significant amounts of inorganic salts as byproducts.

Fine chemicals are predominantly (but not exclusively!) the domain of homogeneous catalysis, where solvents present another issue of environmental concern. According to Sheldon, the best solvent is no solvent, but if a solvent is unavoidable, then water is a good candidate. [R.A. Sheldon, *J. Chem. Tech. Biotechnol.* **68** (1997) 381].


Sheldon has introduced several indicators to measure the efficiency and environmental impact of a reaction. The atom efficiency is the molecular weight of the desired product divided by the total molecular weight of all products. For example the conventional oxidation of a secondary alcohol




has an atom efficiency of $360/860 = 42\%$. By contrast, the catalytic route



offers an atom efficiency of $120/138 = 87\%$, with water as the only byproduct. The reverse step, a catalytic hydrogenation, proceeds with 100% atom efficiency:



as does the catalytic carbonylation of this molecule:



Another useful indicator of environmental acceptability is the *E* factor – the weight of waste or undesirable byproduct divided by the weight of the desired product. As Tab. 1.1 shows, the production of fine chemicals and pharmaceuticals generate the highest amounts of waste per unit weight of product. Atom efficiencies and *E* factors can be calculated from each other, but in practice *E* factors can be higher due to yields being less than optimum and reagents that are used in excess. Also, loss of solvents should be included, and perhaps even the energy consumption with the associated generation of waste CO_2 .

Table 1.1. Environmental acceptability of products in different segments of the chemical industry (from R.A. Sheldon, *Chem. Ind.* (1997) 12 and (1992) 903).

Industry segment	Product tonnage	<i>E</i> factor kg waste/kg product
Oil refining	$10^6\text{-}10^8$	<0.1
Bulk chemicals	$10^4\text{-}10^6$	<1 – 5
Fine chemicals	$10^2\text{-}10^4$	5–50
Pharmaceuticals	$10\text{-}10^3$	25–>100